



福立特環保科技有限公司
FILTER Environmental Technology Co., Ltd.

SPECIFICATION-
TF-2415

ITEM	VALUE	UNIT
FIBER (纖維)	Polyester (PET) 聚酯纖維	
WEIGHT (克重)	310	g/m ²
THICKNESS (厚度)	0.56	mm
DENSITY (密度)	經向	87.7 (根/吋)
	緯向	57.7 (根/吋)
AIR PERMEABILITY (透氣度)	8.5	cc/cm ² sec@12.7mmH ₂ O
TENSILE STRENGTH(warp 經) (拉伸強度)	1880	N/3cm
TENSILE STRENGTH(filling 緯) (拉伸強度)	1400	N/3cm
ELONGATION AT BREAK(warp 經) (斷裂伸長率)	30	%
ELONGATION AT BREAK(filling 緯) (斷裂伸長率)	35	%
CONTINUOUS SERVICE TEMPERATURE (連續使用溫度)	140	°C
FINISH (處理)	(熱定型 hear setting)	
SHRINKAGE LENGTH(warp 經) (熱收縮)	6.00	140°C / 1hr 20MM*24MM
SHRINKAGE LENGTH(filling 緯) (熱收縮)	5.00	140°C / 1hr 20MM*24MM
ELASTICITY(warp 經) (抗拉伸率)	3.2	*at 50N
ELASTIC(filling 緯) (抗拉伸率)	8.5	*at 50N